

# Coir Fibre Reinforced Flyash Based Geopolymer Concrete

Dharashree<sup>1</sup>, Biswajit Nayak<sup>2</sup>

1( Department of Civil Engineering, Gandhi Engineering College ,Odisha, India)

2(Department of Civil Engineering, Gandhi Institute For Technology, Odisha, India)

---

**ABSTRACT:** Objective: To research the conduct of coir fiber as support in geopolymer concrete. Investigation: Low-calcium fly debris is utilized as the creation of geopolymer concrete. Before utilizing in solid coir fiber is treated with latex glue arrangement. Coir fiber of length 25mm with different rates i.e., 0%, 0.75%, 1.5%, 2.25%, 3% are utilized. The blend of Na<sub>2</sub>SiO<sub>3</sub> arrangement & NaOH result was utilized for fly debris enactment. Restricting operator to fly debris proportion was 0.45. The molarity utilized was 12M (Molars). Surrounding restoring is followed for this work. Discoveries: The different quality parameters were tried at different ages i.e., 7, 14 and 28 days. Applications: Coir fiber which is going about as support added to oppose the small scale splits. So this can be relevant where the necessity to oppose the small scale splits.

**Key words:** Fly ash, Latex liquid, NaOH, Na<sub>2</sub>SiO<sub>3</sub>, Coir fiber

---

## I. Introduction

The inorganic aluminosilicate polymer, called geo-polymer which efforts to create ecological concrete which is synthesized from by-product of materials like fly ash which is high in silicon & aluminum. Geo-polymer was introduced in 1978, to explain about the mineral binders with alkaline<sup>1</sup>. Geo-polymer has two constituents they are basic materials & alkaline liquids. The basic materials are high in Si & Al. Fly ash constitutes of high amount of Si-Al materials, it has high cementations property, and fly ash is by-product of coal that is available in thermal powerplant<sup>1</sup>.

To increase the life of structure is by using bond fiber polymer composites onto the structure. By this the tensile strength and the toughness of the structure increase and it improves deformation characteristics and minimizes the cracking effect of the structure. When these fibre composites are Experimental Study On Coir Fibre Reinforced Flyash Based Geopolymer Concrete with 12m Molar Activator exposed to marine environment they are suffering from degradation because of surface blistering. Due to this degradation the adhesive bond strength is reduced and delamination about composites occurs. A further way is to restore steel bars by means of fibers to create a fiber reinforced concrete (FRC)<sup>2</sup>.

This type of reinforcing concrete improves the non-reinforced concrete properties which is highly brittle. Enough natural resources are available and researching on these natural resources is going on. Growth of natural fiber composite<sup>3</sup> recently started. These fibers have high in impact strength but have moderate flexural and tensile properties and these are eco-friendly materials. Utilizing of coir fiber as low cost building materials<sup>4</sup> is increased. The presence of fiber improves the ductility of mix, tensile and flexural strengths of mix, fracture roughness. Natural rubber latex is used for the treatment of coir fiber.

## II. Methodology

The binder in geo-polymer concrete is fly-ash. Fly-ash binds the coarse aggregate, fine aggregate to form geopolymerization<sup>5</sup>. Coir dust and pith is to be separated from coir fiber and 25mm of length to be considered. The chopped coir fiber is soaked in solution which is prepared by combination of water and sodium hydroxide. For the preparation of soaking solution for one liter of water we have added sodium hydroxide of 5%. This soaking is allowed for 48 hours so that the coir fiber is to mercerization<sup>10</sup>. After 48hrs coir fiber is washed repeatedly with distilled water and allowed to dry for 24hrs. Now the coir is soaked in latex compound which is combination of 70% of rubber latex, 10% of NaOH solution and 20% of distilled water for 15min and dried for 24hrs. In this research 20% of metakaolin is added to the amount of powder content for the purpose of one day setting only not for strength parameters.

### 2.1. SOURCE MATERIALS

**2.1.1. Fly ash:** The combustion of ground or powdered coal which results the residue of finely divided particle is known as fly ash. The combination of oxides of Calcium (CaO), Aluminum (Al<sub>2</sub>O<sub>3</sub>), Silicon (SiO<sub>2</sub>), and Iron (Fe<sub>2</sub>O<sub>3</sub>), are the chemical compositions, where the percentage of Titanium, Sodium, and Magnesium, Potassium, Sulphur are present in lesser amount. Fly ash is preferred is Low-calcium (ASTM Class F) as shown in Figure 1.



**Figure 1 FLYASH**

**2.1.2. Alkaline Liquids:** For geo-polymerization the mixture of NaOH and Na<sub>2</sub>SiO<sub>3</sub> is used. In polymerization process alkaline liquid plays a key role. To prepare NaOH concentration either flakes or pellets are allowed to dissolve in water. For 12M, to prepare NaOH concentration,  $12 \times 40 = 480$  grams of flakes per liter of the solution, where 40 is the molecular weight of NaOH.

**2.1.3. Coarse aggregates:** The coarse aggregate 10 mm was used for this experimental work which is locally available.

**2.1.4. Fine aggregates:** The locally available river sand, passing through 4.75 mm was used in this experimental work.

#### **2.1.5. Coconut Fiber**

Coir fibre has the potential to be used as reinforcement in internal wall paneling<sup>7</sup> system with binder component of cement and gypsum. Coir fibre is extracted from coconut outer shell. Coir fiber is chopped of 25mm as shown in Figure 2. and various percentages of 0%, 0.75%, 1.5%, 2.25%, 3% is used for this research.



**Figure 2 COIR FIBER**

**2.1.6. Metakaolin:** The Metakaolin is used for the investigation. The particle size of the metakaolin was referred with the help of scanning electron microscope. In powder content 20% is used as metakaolin for the setting purpose only.

**2.1.7. Latex Rubber:** Latex is a polymer of micro particles in an aqueous medium. It is either in natural or in synthetic form. Latex in nature is milky fluid as shown in Figure 3. Latex consists of tannins, sugars, gums, alkaloids, oils, proteins, resins, and starches that coagulate on exposure to air. Naturally available latex is white, but in some plants latex is scarlet latex, orange or yellow.



Figure 3 LATEX LIQUID

## 2.2. COMPOSITE PREPARATION

The coir fiber is chopped to 25mm. The chopped fibers are allowed to soak in sodium hydroxide for 48hours for chemical treatment. After 48hours the treated coir fibre is washed repeatedly and allowed to dry for 24 hours. The dried fibres are then resin with latex compound the combination of 70% of latex, 10% of sodium hydroxide solution and 20% of water to achieve the homogenization and allowed to dip for 15 minutes and dried for 24 hours. Experimental Study On Coir Fibre Reinforced Flyash Based Geopolymer Concrete with 12m Molar Activator Polymerization is formed by the mixing of  $\text{Na}_2\text{SiO}_3$  and  $\text{NaOH}$ . Sodium hydroxide is in the form of pellets or flakes. To form 12M, the sodium hydroxide flakes of 480 gms are dissolved in water to require the concentration. During the formation of concentration it liberates large amount of heat. To form polymerization the mixed sodium silicate and sodium hydroxide are allowed to keep at room temperature for minimum of 24hrs. This mixed solution acts as a binding agent.

## 2.3. MIXING, CASTING AND CURING

The  $\text{Na}_2\text{SiO}_3$  and  $\text{NaOH}$  are mixed one day before to get polymerization which is perfectly suitable as the binding agent. All the materials are mixed manually. Fly ash and aggregate are mixed for one minute and the binding agent is added with small amounts and the mixing is done for 2minutes. Now the treated fibres are added to the mixture with the slow increment and mixing is done thoroughly. For compressive test cube specimens of  $150 \times 150 \times 150 \text{mm}$ , for split tensile test<sup>9</sup> cylindrical specimens of 150mm dia and 300mm height specimen and for flexural strength beam specimens  $100 \times 100 \times 500 \text{mm}^3$  were casted. Curing is done under ambient conditions<sup>8</sup>.

## III. RESULTS AND DISCUSSIONS

### 3.1. COMPRESSIVE TEST

The Figure 4. shows that the strength of the specimen increases upto a level and then the strength falls down. For 7 days the maximum strength obtained is  $7.3 \text{ N/mm}^2$ . For 14 days  $9.45 \text{ N/mm}^2$  and for 28 days  $10.58 \text{ N/mm}^2$  are the maximum strengths obtained. This shows that optimum percentage of coir fiber is 2.25 for all.




Figure 4 Compressive strength

### 3.2. SPLIT TENSILE TEST

The Figure 5. shows that the strength of the specimen increases up to a level and then the strength falls down. For 7 days the maximum strength obtained is  $0.378 \text{ N/mm}^2$ . For 14 days  $0.41 \text{ N/mm}^2$  and for 28 days  $0.48 \text{ N/mm}^2$  are the maximum strengths obtained. This shows that optimum percentage of coir fiber is 2.25 for all.




Figure 5 Split tensile strength

### 3.3. FLEXURAL STRENGTH

The Figure 6. shows that the strength of the specimen increases up to a level and then the strength falls down. For 7 days the maximum strength obtained is 1.76 N/mm<sup>2</sup>. For 14 days 2.26 N/mm<sup>2</sup> and for 28 days 2.93 N/mm<sup>2</sup> are the maximum strengths obtained. This shows that optimum percentage of coir fiber is 2.25 for all.




Figure 6 Flexural strength

## IV. CONCLUSIONS

1. The propagation micro cracks are resisted.
2. Optimum percentage of coir fiber is 2.25 in this research.
3. Increase in coir fiber percentage the strength parameters are also increase up to optimum and then strength decreases.
4. For 28 days 2.25% of coir fiber the compressive strength is 11.65% more comparing to 0% of coir fiber.

Experimental Study On Coir Fibre Reinforced Flyash Based Geopolymer Concrete with 12m Molar Activator

5. For 28 days 2.25% of coir fiber the split tensile strength is 41.65% more comparing to 0% of coir fiber.
6. For 28 days 2.25% of coir fiber the flexural strength is 37.9% more comparing to 0% of coir fiber.

**REFERENCES**

- [1] Pravin V D. Improvement in the strength of concrete by using industrial and agricultural waste. International organization of Scientific Research (IOSR) Journal of Engineering. 2012 April; 2(4), 755-759.
- [2] Tara Sen, Jagannatha Reddy H N. Application of sisal, bamboo, coir and jute natural composites in structural upgradation. International Journal of Innovation, Management and Technology. 2011 June; 2(3), 186-191.
- [3] Krishnan L, Karthikeyan S, Nathiya S, Suganya K. Geopolymer concrete an eco-friendly construction material. International Journal of Research in Engineering and Technology. 2014 June; 3(11), 64-67.
- [4] Raijiwala D B, Patil H S. Geopolymer concrete: a concrete of next decade. Journal of Engineering Research and Studies. 2011 March; 2(1), 9-25.
- [5] Prof. More Pratap Kishanrao. Design of geopolymer concrete. International Journal of Innovative Research in Science, Engineering and Technology. 2013 May; 2(5), 1841-1844.
- [6] Sahaya Ruben J, Baskar G. Experimental study of coir fiber as concrete reinforcement material in cement based composites. International Journal of Engineering Research and Applications. 2014 January; 1(3), 128-131.
- [7] Aditya Varma K.V, Manideep T and SS. Asadi. A Critical Comparison of Quantity Estimation for Gated Community Construction Project Using Traditional Method Vs Plan Swift Software: A Case Study. International Journal of Civil Engineering and Technology, 7(6), 2016, pp. 707– 713
- [8] G.S. Sarma, SS. Asadi and S. Lakshmi Narayana, Creation of Web Based Decision Support Information System for Evaluation of Topographic Characteristics Using Remote Sensing & GIS and Visual Basic Programe. International Journal of Civil Engineering and Technology, 7(6), 2016, pp. 621–634
- [9] Vinod B S, Kalurkar L G. Effect of different types of steel fibers with metakaolin & fly ash on mechanical properties of high strength concrete. International Journal of Civil Engineering & Technology, 2013 May; 4, (3), 73 - 79.
- [10] Varun Teja T and SS Asadi, An Integrated Approach for Evaluation of Environmental Impact Assessment-A Model Study. International Journal of Civil Engineering and Technology, 7(6), 2016, pp. 650–659
- [11] Bakharev T. Geopolymeric materials prepared using class f fly ash and elevated temperature curing. Journal of Cement and Concrete Research. 2005; 35, 1224-1232.
- [12] Huang G. Tensile behaviours of the coir fibre and related composites after NaOH treatment. Materials and Design. 2009; 30, 3931-3934.
- [13] Romildo D, Toledo Filho, Karen Scrivener, George L E, Khosrow Ghavami. Durability of alkali-sensitive sisal and coconut fibres in cement mortar composites. Cement& Concrete Composites.2003; 27, 527-536.